global sourcing **to** local reliability

PRODUCT SPECIFICATION

PRODUCT : Lithium Carbonate Technical Grade 60 mesh - 250 micron

DOC. No. : SV 030 REV 06

Li_2CO_3	99% min
Fe_2O_3	0,01% max
CaO	0,05% max
Cl	0,05% max
SO_4	0,35% max
H_2O	0,6% max
Na_2O	0,2% max
Insoluble in HCL	0,02% max
Bulk density	0,8 g/cm^3
Molecular weight	73,89
Density 20°C	2,049 g/cm^3
Standard heat of formation	290,64 +/- 0,04 kcal/mole
Standard heat of fusion	10,7 +/- 0,1 kcal/mole
Specific heat 25°C	0,453 cal/g/Celsius

Typical Particle size distribution:
100% through 60 mesh sieve

Rodachem B.V.
Hogerwerf 1
4704 RV Roosendaal
The Netherlands

T +31(0)165 581888
F +31(0)165 561197
E info@rodachem.nl
www.rodachem.nl

ABN-AMRO Bank N.V. Amsterdam
REK/ACC EUR no 24.46.56.762
REK/ACC USD no 24.21.17.309
REK/ACC GBP no 24.21.17.295

SWIFT: ABNANL2A
IBAN NO: NL06ABNA0244656762
IBAN NO: NL11ABNA0242117309
IBAN NO: NL98ABNA0242117295

Btw/vat-no:
NL813971974B01
Reg. no: 20051548

Responsible Care

kiwa certified ISO 9001

ONZE IN- EN VERKOOPVOORWAARDEN ZIJN GEDEPONEERD BIJ KAMER VAN KOOPHANDEL BREDA ONDER NR 20051584. OP UW VERZOEK ZENDEN WIJ U HIERVAN EEN EXEMPLAAR TOE.
OUR CONDITIONS OF PURCHASE AND SALE HAVE BEEN FILED WITH CHAMBER OF COMMERCE BREDA UNDER REG.NO 20051584. COPY OF WHICH WILL BE SENT TO YOU ON YOUR REQUEST

THIS INFORMATION IS BELIEVED TO BE TRUE AND ACCURATE. USERS ARE SOLELY RESPONSIBLE FOR ENSURING THAT THIS PRODUCT MEETS THEIR PARTICULAR NEEDS AND SPECIFICATIONS. RODACHEM BV CANNOT BE HELD RESPONSIBLE FOR ANY LOSS, DIRECT OR INDIRECT, RELATED TO THE USE OF THIS PRODUCT. OUR GENERAL CONDITIONS OF SALE, DOC 07.05 REV 03 ARE APPLICABLE. YOUR CONDITIONS ARE DECLINED.